

GRANULE APPLICATION SPECIFICATION



HAND APPLICATION

Broadcast by hand until surface is saturated with granules. Let dry and remove any excess granules. Min rate is 35 lbs per roofing square.

SUGGESTED APPLICATION EQUIPMENT AND COVERAGES

1. Six bags of granules into sand blasting pot with appropriate regulated air.
2. One and a quarter inch OD clear vinyl hose capable of handling (3) three times the operating pressure. (Note: granules are dispersed at relatively low air pressure DO NOT USE FOR SANDBLASTING)
3. Application rate can vary depending upon gallons of coating applied. Typical coverage using this method is 40 to 50 pounds per roofing square

TECHNICAL DATA

Properties Average Bag Net Weight 80 lbs. Number of Bags/Pallet 35 - 2,800 lbs. Truckload 15 - 18 pallets Color Bright White Bulk Density 90 - 100 lbs/cu ft Particle Size 1 - 2mm

These products are for industrial/commercial applications only. These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use are beyond our control

