

PG 2400 HT ELASTOMERIC ROOF COATING



HIGH TENSILE ACRYLIC ELASTOMERIC ROOF COATING

PRODUCT DESCRIPTION

- Highest performance, plasticizer free, single component, water-based, 100% acrylic elastomeric coating for spray brush or roller application.
- Industry leading tensile and elongation properties contribute to an extremely durable and long lasting membrane with exceptional resistance to weathering.
- Formulated utilizing special pigments and biocides to provide maximum UV resistance along with a polymer technology that sets the standard for roof coating resistance to discoloration from dirt accumulation.
- Has excellent adhesion to most surfaces including metal, most single-ply roofs, wood and concrete.
- Has the unique ability to “breath”, providing a completely watertight membrane while allowing trapped moisture to escape.

PERFORMANCE CHARACTERISTICS

PG 2400 HT is designed as a protective membrane for most roofing surfaces including galvanized metal, concrete, PVC, Hypalon, EPDM, polyurethane foam and primed smooth and granulated asphaltic surfaces. Check with your ProGuard representative for primer recommendations.

COLORS

Standard Colors: White, Gray and Tan
Special Colors are available for an additional charge.

PACKAGING/SHIPPING INFORMATION

CONTAINER SIZE	SHIPPING CLASS
55 Gallon drum (208.2 liters)	Class 55
5 Gallon pail (18.9 liters)	Class 55

SURFACE PREPARATION

General: Surfaces to be coated should be dry, free of dust, dirt, oil, loose granules, gravel, peeling coating and other foreign matter. All wet insulation or foam should be removed and replaced with like materials. For optimal results power wash all surfaces with a minimum of 2000 psi using a wide fan tip. All necessary precautions should be taken to avoid damage to the roof system. Mildew should be treated with a bleach solution (1 part Bleach, 2 parts water) and rinsed thoroughly. Patch and repair cracks or holes with appropriate sealants or caulking materials.

Masonry: Allow fresh masonry to cure a minimum of 30 days. Check with your ProGuard representative for primer recommendations.

Metal: Rusty metal must be cleaned with a wire brush and primed with primed with PG 1200 DTM primer.

PHYSICAL PROPERTIES

PROPERTIES	TEST METHOD	RESULT
Volume solids	ASTM D-1653	55.0 ± 2%
Weight Solids	ASTM D-1644	66.0 ± 2%
Tensile Strength	ASTM D-2370	500 ± 50 PSI
Elongation	ASTM D-2370	600 ± 50%
Permeability	ASTM D-1653	14 ± 3
Tear Resistance	ASTM D-624	133 ± 3 PSI
VOC	EPA Method 24	< 50 g Liter
Low temperature Flexibility	(-15°, 1/2 in mandrel, 1000hrs weathering)	Pass
Hardness (Shore A)	ASTM D-2240	50 - 55
Reflectivity	ASTM C-1549	87%
Emittance	ASTM C-1371	.90
SRI	Calculated	107
Viscosity		110 ± 10 KU
Density		11.1 lbs per gallon
Flashpoint		None
Shelf Life		6 months
Clean Up		Water

MEETS REQUIREMENTS FOR ASTM D6083 ACRYLIC ELASTOMERIC ROOF COATING

EPDM: Wash with PG EDPM Primer /Cleaner, ensure no primer residue remains.

PVC, Hypalon, aged TPO: Prime with ProGuard SP.

Polyurethane foam: Apply directly (must be coated within 24 hours of installation).

Granulated Asphalt: Coat with PG 2050 Bleed block primer.

Smooth Asphalt: Base coat with PG 2050 Bleed Block primer.

PG 2400 HT ELASTOMERIC ROOF COATING

GENERAL PURPOSE ALL ACRYLIC ELASTOMERIC ROOF COATING

APPLICATION

This product may be brushed rolled or sprayed on a clean, dry surface. For details see Equipment Recommendations at the end of this sheet. Before applying additional coats, the previous coat must be completely dry and cured. If any contamination is present on the cured surface it must be washed and completely dry before application of subsequent coats.

APPLICATION PROPERTIES

Yield (1 gal to 100 sq ft)	8.8 dry mils
Dry Time (75° F)	90 mins @ 50% humidity
Recoat window	> 6 hrs
Complete Cure	30 days

COVERAGE RATE:

Apply PG 2400 Base Coat at the rate of 1.5 gallons per 100 sq. ft. (24 wet mils). Surface texture and wind will affect applied mil thickness.

ENVIRONMENTAL CONDITIONS

This product cures by water evaporation only. Product must not be applied when the ambient temperature is below 50°F or if there is any possibility it could fall below 32°F within 24 hours of application. Application is not recommended if rain or dew is likely to occur before product dries. In high humidity conditions late afternoon applications should be avoided as overnight dew formation on uncured surface can cause coating wash-off. On marginal days, multiple applications of thin coats can ensure proper drying before rain or overnight freezes.

PONDED WATER

- ProGuard Group warranties do not cover damage due to ponding water.
- The National Roofing Contractors Association considers ponding water on any roof unacceptable. (See the NRCA Roofing and Waterproofing Manual).

LIMITATIONS

Surface must be clean and dry. Application is not recommend on roofs with slopes less than 1/8 in 12 or where ponded water is present. Do not apply over wet substrates or when inclement weather is imminent. Complete cure of PG 2400 Base Coat requires complete evaporation of water. Cool temperatures and high humidity retard cure. In addition, this product is not recommended for use without a vapor barrier in cryogenic tank or cold storage roofing applications. It is not intended for use as a thermal barrier.

SAFE PRACTICES

This product is designed for professional installation. Before working with this product, you must read and become familiar with the available information on its risks, proper use and handling. Information sources include but are not limited to MSDS and product labels. More resources are available at polyurethane.org, sprayfoam.org, everestsystemsco.com or by contacting ProGuard Group directly.

EQUIPMENT

Minimum requirements:

Brush: Synthetic filament

Roller: 1/4" nap roller

Airless Spray: Equipment capable of maintaining a minimum of 0.027" or greater orifice tips with 2,300 PSI at the tip. Filter screens should be thirty-mesh or larger.

Contact your ProGuard Group representative for specific recommendations, pricing on airless equipment.