

## INSTALLATION GUIDE SPECIFICATION FOR RESTORATION OF EXISTING METAL ROOFS (10 YEAR WARRANTY)

### WARRANTY

#### PART 1 - GENERAL

##### 1.01 SUMMARY

- A. PG 9600, manufactured by ProGuard Group, Inc., is a high solids, solvent-free, alkoxy-based silicone roof coating which moisture cures to a durable, breathable, waterproof barrier which is highly resistant to degradation from UV and natural weathering. PG 9600 may be used to top coat concrete roof substrates for restoration and longevity.
- B. Scope: Installation of PG 9600 silicone roof coating, labor and accessory materials.
- C. Exclusions: This guide specification does not include: repair or replacement of roof accessory items such as vents, expansion joints, drains, penetrations and mechanical equipment; evaluation and correction of roof load capacity or wind uplift resistance.

##### 1.02 SUBMITTALS

- A. Product Data: Technical Data Sheets and SDSs for all products used on project.
- B. Shop Drawings: Drawings indicating scope of work and roofing details.
- C. Samples: Cured coating samples.
- D. Sample Warranty (optional; see Section 1.06)

##### 1.03 QUALITY ASSURANCE

- A. Manufacturer Qualifications: PG 9600 high solids, silicone roof coating supplied and manufactured by PGG (ProGuard Group, Inc.) are approved for and shall be used on this project. Upon request, PGG will provide certification that all PGG materials meet the physical properties required by the specification.
- B. Adhesion Test: Prior to estimating coating restoration project, conduct an adhesion test in accordance with PGG adhesion testing procedures to determine if a primer or other specific surface preparation is required.
- C. The silicone coating manufacturer shall have a minimum of 20 years' experience in the manufacture of silicone roof coatings. The coating shall have an Underwriters Laboratories (UL) Listing.
- D. Contractor Qualifications: The contractor shall be approved by PGG and eligible to offer a PGG Silicone Ten (10) year Labor & Material Warranty.
- E. Deviations: Any deviation from this specification must be approved in writing by PGG.
- F. Field Quality Control: Upon completion of the roof coating project, an inspection by PGG's designated third-party inspection agency may be required. Consult with PGG for specific requirements.

##### 1.04 DELIVERY, STORAGE AND PROTECTION OF MATERIALS

- A. Delivery: All products shall be delivered in the original, factory-sealed drums, pails or other containers. All product containers shall be labeled with the manufacturer's name and address, product name and description, product date/expiration date and batch/lot number.

- B. Materials damaged during shipment, delivery or storage shall not be used on this project without approval of PGG.
- C. Handling and Storage: Store PG 9600 containers between 15°F-109°F (9.44°C-42.78°C). Other materials shall be stored in accordance with the appropriate material's TDS. Keep all products out of direct sunlight and protected from extreme temperatures.
- D. SDSs and TDSs for all materials used on this project will be kept on site and reviewed by appropriate personnel before use.

## 1.05 GENERAL SITE CONDITIONS

- A. All mechanical units, skylights, vents and other protrusions and other rooftop accessories should be in place prior to surface preparation and coating application commences.
- B. All mechanical units should be adjusted or shut down to prevent fumes and odors from entering the facility.
- C. Mask or otherwise protect all surfaces not to be prepared and/or coated to prevent overspray damage. Use wind screens as appropriate.
- D. Review existing and imminent weather conditions (including potential for extreme temperatures, relative humidity, frost, dew, and precipitation) to assure that coating and accessory material will have sufficient curing time.
- E. Temperature at the time of application of the PG 9600 roof coating application should be above 15°F (9.44°C) to allow coating to cure properly.
- F. Apply PG 9600 roof coatings only to clean, dry and secure surfaces.
- G. Protect PG 9600 roof coating from foot traffic or other potential abuse during the curing process. The coating is considered cured when it is tack free and sufficiently durable to withstand roof traffic.
- H. All work performed under this specification must be in accordance with all appropriate local, state and federal regulation.
- I. While cured PG 9600 roof coating is unaffected by ponding water conditions, various professional roofing associations (including NRCA) consider ponding water undesirable and recommend that roofs be designed for positive drainage. Corrective action should be considered, prior to application of PG 9600 roof coating, to correct existing ponding conditions and/or drainage deficiencies.

## 1.06 WARRANTY INFORMATION

- A. A manufacturer's limited labor & material warranty is available on eligible projects. Contact PGG Technical Support for details.
- B. Limited warranties are not available for continuous immersion service: cryogenic, freezer or cold storage facilities; or over existing wet roofing materials. Other limitations may apply.
- C. Inspections: Warranted projects are subject to:
  - 1. Pre-job inspection and adhesion test; and
  - 2. Final quality control inspection.
  - 3. Inspections may be performed by PGG or its designated third-party inspectors at PGG's discretion.
- D. Warranty submittals
  - 1. PGG Warranty Pre-Approval Application
  - 2. Adhesion test results

## PART 2 - PRODUCTS

### 2.01 SILICONE COATING

- A. PG 9600 high solids, solvent-free, alkoxy-based, moisture-cured, silicone roof coating supplied and manufactured by ProGuard Group, Inc., Los Angeles, CA.
- B. Physical Properties shall be tested in accordance with ASTM D6694 as indicated in the table below.

PROPERTY	ASTM STANDARD	VALUE
Tensile Strength	D2370	200 psi min
Elongation at Break (73°F)	D2370	500% min
Volume Solids	D2697	90% min
Weight Solids	D1644	90% min

## 2.02 SEAM TREATMENT MATERIALS

- A. ProGuard 1395 Gel, ProGuard Group, Los Angeles, CA. Refer to the ProGuard 1395 Gel Technical Data Sheet for physical property information.
- B. UltraSpan UST / USM pre-cured silicone transition sheets and molded corners, ProGuard Group, Los Angeles, CA. Refer to the UltraSpan Technical Data Sheet for physical property information.
- C. CAULK/SEALANT: SCS2000 SilPruf silicone sealant and adhesive, ProGuard Group, Los Angeles, CA. Refer to the SCS2000 Technical Data Sheet for physical property information.
- D. Polyester Fabric: Hanes stitch-bonded polyester reinforcing fabric in 4.0", 6.0" or 12.0" widths. Refer to the Hanes Fabric Technical Data Sheet for physical property information.

## 2.03 ACCESSORY MATERIALS

- A. Traffic Mats: Yellow Spaghetti (manufactured by Western Plastics, Inc. 800-325-3605) pressure bonded, non-woven pads (or in rolls) made of spaghetti like strands of flexible polyvinyl chloride, nominal thickness 5/16".
- B. Yellow Walkway Coating: GE SEC2400 Protection Yellow Silicone Coating

## PART 3 - EXECUTION

### A. GENERAL

- Existing roofing materials shall be securely fastened to meet wind uplift requirements.
- All roofing surfaces shall be free of loose material, grease, soft asphalt, and other materials that could interfere with adhesion.

### B. METAL

- Metal that has corroded to the point of weakness must be replaced.
- All rusted metal surfaces shall be primed with PG Rust Inhibitive Primer at a rate of approximately 1 gallon per 200 sq ft.
- Ferrous Metal: Remove loose rust and unsound primer from shop primed iron and steel surfaces by scraping, wire brushing, or sandblasting. Prime according to MPM recommendations.
- Non-Ferrous Metal: Clean and prime galvanized metal, aluminum, copper, and stainless steel surfaces and prime as recommended by MPM.
- Tighten or replace all fasteners as necessary. In no case shall joints or seams be allowed to separate greater than 1/16 inch.
- If roof has surface clips they must be encapsulated with fabric and coatings using the same method as the seams. Special care must be taken to avoid air entrapment under the fabric. Special care must also be taken to allow water to flow around clips. If damming occurs water will collect above clips and may cause staining of the film over time.
- Seam caps should be sealed on each edge using the same method as the seams.
- If the metal surface is free of loose scale, rust, weathered or chalking paint, it can be cleaned using compressed air jet, vacuum equipment, or broom to remove loose dirt. Grease, oil, or other contaminants shall be removed with proper cleaning solutions.

9. Seal all joints and seams with Hanes polyester fabric and PG 9600 as described below:
  - 1) Apply basecoat in a four (4.0") inch wide strip over the seam at a rate of 1.5 gallons/sq.
  - 2) In the wet coating, embed the four (4.0") inch wide polyester fabric
  - 3) Immediately spray a six (6.0") inch wide layer of PG 9600 basecoat at a rate of 1.0 gallons/sq.
  - 4) Allow to fully cure for 2 to 12 hours.
10. Seal all nails and fasteners with GE SCS2000 SilPruf or GE SS1 as described below.
11. Apply sealant to each fastener.
12. Ensure sufficient sealant is used to completely encapsulate each fastener with no gaps, fishmouths or holes in sealant.
13. Allow to fully cure for 2 to 12 hours.

### 3.02 COATING APPLICATION

- A. The PG 9600 roof coating shall be applied uniformly in one or more coats at a theoretical application rate of 1.5 gal/100 ft<sup>2</sup> to achieve a WFT (wet film thickness) of 24 mils and a minimum total DFT (dry film thickness) of 21 mils. NOTE: Theoretical coating application rate is based strictly on minimum wet film thickness requirements and must be increased for site-specific conditions such as surface texture, overspray loss, container and other residues, application technique and environmental conditions.
- B. Required final DFT is 21 mils minimum on any given area of the roof surface. Apply additional coating as needed to meet this requirement.
- C. Additional coats: When additional applications of coating are needed, allow sufficient cure time between applications to provide a stable working surface. Subsequent coating should be applied in a spray, roller or brush pattern perpendicular to the previous application.
- D. Equipment: PG 9600 may be applied by spray equipment, roller or brush.
- E. Cure: PG 9600 cures by reacting with ambient moisture. Cure time will be reduced at elevated ambient humidity and temperatures.

### 3.03 FINISHED COATING MEMBRANE CHARACTERISTICS

- A. The cured PG 9600 membrane should be monolithic and seamless, encapsulating the entire existing concrete surface. The coating should be free of holidays, voids, pinholes and cracks. Apply additional coating as necessary to correct defects.
- B. Minimum cured coating thickness is 21 mils DFT.

### 3.04 SAFETY REQUIREMENTS

- A. Refer to appropriate SDSs (Safety Data Sheets) for additional safety information.
- B. Before starting to apply coating, primers or other materials, any potential sources of air entry into the building must be sealed off.

### 3.05 CLEANUP

- A. Keep all work areas clean, clear and free of debris at all times.
- B. Do not allow trash, waste or debris to accumulate on the roof. Remove these items from the roof on a daily basis.
- C. Collect and properly store all tools and unused materials at the end of each workday.
- D. Dispose of or recycle all trash and excess material in a manner conforming to current EPA regulations and local laws.
- E. Properly clean the finished roof surface after completion and make sure the drains and gutters are not clogged.
- F. Clean and restore all damaged surfaces to their original condition.

### 3.06 QUALITY CONTROL

# PG 9600 HIGH SOLIDS SILICONE ROOF COATING



A. PG 9600 coating restoration projects are subject to pre-job, progress and final inspections by PGG, its designated third-party inspectors, or others subject to warranty requirements and contract documents.

