

5000 Pond Buster



Rapid Set Roof Leveling Compound

For Professional Use Only

DESCRIPTION

- Two component roof leveling Compound
- Effectively Eliminates ponded areas on roofs
- Fast sure - Can apply any roofing system over Pond Buster in 4 hours.
- Self-leveling - Flows to, and fills, low areas
- Formulated with environmentally friendly renewable components.
- Cures to a flexible highly durable membrane
- Exceptional adhesion to weathered roofing substrates and concrete.
- Waterproof - Extreme water and freeze thaw resistance.
- Lightweight - weighs less than water.
- Easy mix formula
- 100 % solids ensure maximum film build per gallon.
- VOC free, meets even the most stringent VOC regulations.

RECOMMENDED USES

Pond Buster is designed as a fast cure extremely durable self-leveling compound for the elimination of ponded areas on all types of flat roofs.

COLORS

Standard Colors: Gray.

PACKAGING/SHIPPING INFORMATION

CONTAINERS 1 x 4 Gallon Kit Consisting of:

SHIPPING CLASS - 60

1 x 5 Gallon pail Component B containing 3.3 gallons

1 x 1 Gallon bag Component A containing 0.7 gallons

Property	Test Method	Result
Volume solids	ASTM D-1653	100 \pm 2%
Weight Solids	ASTM D-1644	100 \pm 2%
Tensile Strength	ASTM D-638	\pm 1000 PSI
Adhesion (to Concrete)		> 300 PSI
VOC	EPA Method 24	0 g Liter
Hardness (Shore A)	ASTM D-2240-81	60 \pm 5
Viscosity (A component)		200 \pm 50 mPa.s
Viscosity (B component)		2500 \pm 50 mPa.s
Permeance	ASTM E-96	0.02 Perms
Flashpoint		none
Shelf Life		1 Year
Density		7.1 lbs/gallon
Mix ratio (by volume)		1 "A" : 4 "B"

PROGUARD BUILDING • 2930 Supply Ave • Commerce, CA 90040
www.PROGUARDBUILDING.com • Phone 844-776-4273

Rapid Set Roof Leveling Compound

SURFACE PREPARATION

General: Surfaces to be coated should be dry, free of dust, dirt, oil, peeling coating and other foreign matter. For optimal results power wash all surfaces with a minimum of 2000 psi using a wide fan tip. All necessary precautions should be taken to avoid damage to the substrate.

Mildew should be treated with a bleach solution (1 part Bleach, 2 parts water) and rinsed thoroughly. Patch and repair cracks or holes with appropriate sealants or caulking materials.

Masonry: Allow fresh masonry to cure a minimum of 30 days, check for PH level; higher than 12 call your PG Rep.

Metal: Rusty metal must be cleaned with a wire brush, washed and let dry.

Other: For brand new and other substrates consult your PG representative for primer recommendations.

APPLICATION/Mixing Instructions

1. Stir B component with drill mixer to achieve surface movement for 2 minutes.
2. While continuing mixing add the whole 1 gallon of the A component and continue mixing until completely mixed in, this will take 3 to five minutes.
3. Pour the mixture onto the area to be leveled and squeegee into desired area if necessary.
4. Apply additional buckets of Pond Buster as required.
5. Pot life will be approximately 25 minutes.
6. Continue with roofing system installation once material is tack free to the touch, typically within 60 minutes.

Application properties

Yield (1 gal to 100 sq ft)	16.0 dry mils
Gel Time (75° F)	+ 40 minutes
Tack Free (75° F)	+ 4 hours
Pot life (5 gallons @ 75° F)	20 minutes
90% Cure	24 hours

COVERAGE RATE:

Apply Pond Buster as necessary, at any thickness.

4.0 gallons to 50 sq ft. yields 1/8" thickness

4.0 gallons to 25 sq ft. yields 1/4" thickness

4.0 gallons to 13 sq ft. yields 1/2" thickness

To the best of our knowledge all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact Proguard Building to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Proguard Building. We assume no responsibility for coverage, performance or injuries resulting from use. Liability if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY PROGUARD BUILDING EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE

LIMITATIONS

Surface must be clean and dry. Do not apply over wet substrates or when inclement weather is imminent.

SAFE PRACTICES

This product is designed for professional installation. Before working with this product, you must read and become familiar with the available information on its risks, proper use and handling. Information sources include but are not limited to MSDS and product labels. More resources are available at, proguardbuilding.com or by contacting Proguard Building directly.

WARNING: Individuals with chronic respiratory problems or prior respiratory reactions to such materials should not be exposed to vapors. All personnel entering the application area, including the applicator must wear suitable respirators

EQUIPMENT

Minimum requirements:

- Drill mixer to properly mix 5-gallon pail.
- Squeegee