

PROROF SKYLIGHT



Acrylic Skylight Restorer

For Professional Use Only

DESCRIPTION

- 100% Acrylic UV resistant Technology
- Excellent resistance to dirt pickup, chalking and weathering.
- Rapid drying water-based technology.

RECOMMENDED USES

As a dirt resistant and protective glaze coat for the restoration of weathered skylights.

Property	Result
Total Solids	30% ± 1%
Weight per Gallon	10.7 lbs per gallon ± 0.2
VOC	50 g/liter
Clean Up	Water
Shelf Life-unopened	12 months @ 40-90°F
Viscosity	300 ±100 cP

COLORS

Clear

COVERAGE RATE

Apply ProRoof Skylight at the rate of ½ gallon per 100 sq. ft. (8 wet mils). Surface texture and wind will affect applied mil thickness.

PACKAGING/SHIPPING INFORMATION

CONTAINER SIZE	SHIPPING CLASS
55 Gallon drum (208.2 liters)	Class 55
5 Gallon pail (18.9 liters)	Class 55

ENVIRONMENTAL CONDITIONS

This product cures by water evaporation only. Product must not be applied when the ambient temperature is below 50°F or if there is any possibility it could fall below 32°F within 24 hours of application. Application is not recommended if rain or dew is likely to occur before product dries. In high humidity conditions late afternoon applications should be avoided as overnight dew formation on uncured surface can cause coating wash-off. On marginal days, multiple applications of thin coats can ensure proper drying before rain or overnight freezes.

SURFACE PREPARATION

Surface must be clean, dry and free of loose particles or other foreign matter. If being applied over freshly applied coatings, they must be completely cured before ProRoof Skylight application.

LIMITATIONS

Surface must be clean and dry. Application is not recommended on roofs with slopes less than 1/8 in 12 or where ponded water is present. Do not apply over wet substrates or when inclement weather is imminent. Complete cure of ProRoof Skylight requires complete evaporation of water. Cool temperatures and high humidity retard cure.

APPLICATION

This product may be brushed rolled or sprayed on a clean, dry surface. For details see Equipment Recommendations at the end of this sheet. If sprayed, material should be at least 50°F.

Application Properties

Yield (1 gal to 200 sq ft)	3 dry mils
Dry Time (75° F)	2 to 3 hours
Recoat window	2 to 3 hours
Complete Cure	5 days

PROGUARD BUILDING • 1001 B Ave #100 • San Diego, CA 92118

www.PROGUARDBUILDING.com • Phone 844-776-4273

PROROF SKYLIGHT



Acrylic Skylight Restorer

SAFE PRACTICES

This product is designed for professional installation. Before working with this product, you must read and become familiar with the available information on its risks, proper use and handling. Information sources include but are not limited to SDS and product labels. More resources are available at polyurethane.org, sprayfoam.org, proguardbuilding.com or by contacting Proguard directly.

TECHNICAL DATA SHEET

To the best of our knowledge all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. Used must contact Proguard Building to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Proguard Building. We assume no responsibility for coverage, performance or injuries resulting from use. Liability if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY PROGUARD BUILDING EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE

PROGUARD BUILDING • 1001 B Ave. #100 • San Diego, CA 92118
www.PROGUARDBUILDING.com • Phone 844-776-4273