

## 3000 RAIN-STOP



# High Solids UV Resistant Fibered Silicone Repair Compound

For Professional Use Only

## DESCRIPTION

- A high-solids, single component, moisture cure silicone flashing/repair grade that's ready to use.
- Superior adhesion to damp and even wet surfaces.
- Best-in-class flexibility ensures long-term crack resistance even in high-movement situations.
- Excellent shelf life, typically no mixing required for up to 6 months.
- Excellent sag resistance.
- Superior weathering and excellent water resistance in a breathable membrane.
- Exceptional adhesion to unprimed weathered TPO, PVC, EPDM and SPF.
- VOC compliant.

## RECOMMENDED USES

RAIN-STOP is designed as a UV resistant repair product for most roof membranes. Un-matched adhesion to unprimed aged TPO PVC and EPDM along with excellent performance over Cap sheet, Mod Bit, Metal and Concrete systems.

Property	Test Method	Result
Tensile Strength	ASTM D-2370	205 PSI @ 73°F ± 20
Elongation: (break)	ASTM D-2370	468% @ 73°F ± 50
Tear Resistance: (Die C) lb f/in	ASTM D-624	25
SRI	CRRC	110
Reflectivity (White)	ASTM C-1549	.88
Emissivity: (White)	ASTM C-1371	.90
Permeance US Perms	ASTM E-96 (Procedure B)	6.7
Temperature Stability Range		-80°F to 350°F (-37C to 177C)
Weathering/UV Resistance	ASTM D-6694	No degradation 5000 hours
Specific Gravity		1.30 @ 77°F (25C.)
Tack Free Time	Tem. & Humidity Dependent	20-30 min.
VOC	ASTM D-3960 EPA Method 24	<50 Grams/Liter
Durometer Hardness	ASTM D-2240 Shore A	36
Solids Content by Weight	ASTM D-1644	91%
Solids Content by Volume	ASTM D-2697	90%
Max Continuous Service Temperature		185°F (85C)
Shelf Life - Unopened Containers	6 Months	Stored @ 35°F to 75°F

## COLORS

White,

## PACKAGING/SHIPPING INFORMATION

### CONTAINER SIZE

1, 2 and 5 Gallon pail

### SHIPPING CLASS

Class 55

## SURFACE PREPARATION

**General:** The surface to be coated should be dry, free of dust, dirt, oil, loose granules, peeling coating, or other foreign matter. It may be necessary to power wash and/or prime to enhance adhesion.

# 3000 RAIN-STOP

## High Solids, Silicone Sealant



### APPLICATION

Maximum adhesion will be obtained on clean dry surfaces.

**-Damp Surfaces:** Rain-Stop may be applied to clean damp surfaces when the material is worked in to the substrate with brush or trowel.

**-Wet Surfaces:** For emergency repairs RAIN-STOP can even be applied underwater to stop leaks but it is essential that the material is worked into the leak area to displace the water.

**Note:** Any repairs made in extreme conditions should be reinspected as soon as weather allows.

### Application Properties

Yield (1 gal to 100 sq ft)	15 dry mils
Dry Time (100°F)	2 hours @ 90% Humidity
Dry Time (40°F)	8 hours @ 20% Humidity
Recoat window	>8 hours
Complete Cure	48 hours

### COVERAGE RATE

Typically applied to seams at 48 wet mils (3 gal/sq)

### ENVIRONMENTAL CONDITIONS

The product must not be applied when the ambient temperature is below 35° F.

### PONDED WATER

- The National Roofing Contractors Association considers ponding water on any roof unacceptable.  
(See the NRCA Roofing and Waterproofing Manual).

### LIMITATIONS

The surface should be clean and dry. *Application is not recommended on roofs with slopes less than 1/8 in 12 or where ponded water is present.* In addition, this product is not recommended for use without a vapor barrier in cryogenic tanks or cold storage roofing applications or directly over modified Bitumen, asphalt, or coal tar built-up roofing systems without a sealer. This product carries Class "A" Non-Combustible and Class "B" Combustible credentials as tested under UL 790 procedures over spray foam and single-ply roofing systems. Contact Proguard Building or refer to the UL directory for specific information.

### SAFE PRACTICES

This product is designed for professional installation. Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. Information sources include but are not limited to MSDS and product labels. More resources are available at [polyurethane.org](http://polyurethane.org), [sprayfoam.org](http://sprayfoam.org), [proguardbuilding.com](http://proguardbuilding.com), or by contacting Proguard Building directly.

### EQUIPMENT

Minimum requirements:

#### Brush

- Synthetic filament

### CLEAN UP

Clean spray equipment containing uncured material by flushing with VM&P, Naphtha, or mineral spirits. RAIN-STOP cures by reacting with moisture. Do not leave in spray guns, pump equipment, and hoses for prolonged periods unless the equipment contains moisture lock hoses, fittings, and seals. Without these, the material will cure on hose walls and at unsealed connections possibly causing an increase in operating pressure and material flow restriction.

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. Users must contact Proguard Building to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Proguard Building. We assume no responsibility for coverage, performance, or injuries resulting from use. Liability if any, is limited to the replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY PROGUARD BUILDING EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.